


Coating Data Sheet



Designation

Coating type description OLD	Elastomer
Coating type description NEW	NBR/FSTR

siegling proposition

Design

Coating Material	Nitrile rubber (NBR)
Colour	Green
Surface pattern	Fine structure

Technical data

Hardness [Shore(A)]	65
Density [kg/m³]	
Coating thickness min. [mm]	1.0
Coating thickness max. [mm]	1.0
d factor *	25
Minimum pulley diameter Dmin (approx.) [mm]	[d factor] x [selected coating thickness]
Minimum operating temperature [°C]	-20
Maximum operating temperature [°C]	70

Coefficient of static friction

against PE foil	0.49
against wood	0.64
against sheet glass	0.77
against cardboard	0.72
against aluminium	0.67
against steel sheet	0.83

The physical data in this data sheet is approximate, can alter depending on production environments and was established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN 50014/ISO 554. Fluctuations in climate can cause variations. Temperature range of polyurethane (PU) timing belt base material -5/+80 °C (permanent). See our brochure "Chemical resistance" which shows the resistances of Siegling Proposition (PU) timing belt base material.



siegling proposition timing belts

Coating **Data Sheet**

Properties

Electrostatic properties	non-conductive
Wear resistance	high
Compressibility	No
Product release properties	medium
Cleanability	good

Chemical restistance

General chemical resistance to

Insufficient fat and oil resistance

Special Fabrication

Sanding	No
Milling	No
Punching	Yes

Applications

Glass conveying, Paper / Cardboard conveying

General remarks

Excellent cut and wear resistance.