

# siegling proposition timing belts

# Coating Data Sheet





### Design

Coating Material	Polytetrafluoroethylene (PTFE)
Colour	Grey
Surface pattern	Glossy

#### **Technical data**

Hardness [Shore(A)]	
Density [kg/m³]	
Coating thickness min. [mm]	0.3
Coating thickness max. [mm]	0.3
d factor *	300
Minimum pulley diameter D <sub>min</sub> (approx.) [mm]	[d factor] x [selected coating thickness]
Minimum operating temperature [°C]	-200
Maximum operating temperature [°C]	260

### Coefficient of static friction

against PE foil	0.11
against wood	0.12
against sheet glass	0.11
against cardboard	0.16
against aluminium	0.11
against steel sheet	0.07



# siegling proposition timing belts

# Coating Data Sheet

### **Properties**

Electrostatic properties	non-conductive
Wear resistance	high
Compressibility	No
Product release properties	high release
Cleanability	excellent

#### **Chemical restistance**

General chemical resistance to	Generic fats and oils

### **Special Fabrication**

Sanding	No
Milling	No
Punching	Yes

## **Applications**

Food packaging, Pharmaceutical industry, Conveying of hot and sticky goods

### **General remarks**

Excellent release properties and cleanability. Low friction, accumulation possible. Temperature range limited by PU timing belt material.