

Coating Data Sheet



Designation

Coating type description OLD	Linafood
Coating type description NEW	Linafood

Design

Coating Material	Natural rubber
Colour	White
Surface pattern	Smooth (sanded)

Technical data

Hardness [Shore(A)]	40
Density [kg/m ³]	
Coating thickness min. [mm]	3.0
Coating thickness max. [mm]	12.0
d factor *	20
Minimum pulley diameter D _{min} (approx.) [mm]	[d factor] x [selected belt thickness]
Minimum operating temperature [°C]	-40
Maximum operating temperature [°C]	70

Coefficient of static friction

against PE foil	1.20
against wood	1.25
against sheet glass	1.68
against cardboard	1.14
against aluminium	1.52
against steel sheet	1.46

Coating Data Sheet

Properties

Electrostatic properties	non-conductive
Wear resistance	medium
Compressibility	No
Product release properties	good release
Cleanability	good

Food properties

FDA 21CFR	Qualified for the transport of unpacked Food in compliance with FDA guideline 21CFR
-----------	---

Chemical resistance

General chemical resistance to	Generic fats and oils
--------------------------------	-----------------------

Special Fabrication

Sanding	Yes
Milling	Yes
Punching	Yes

Applications

Food packaging, Vertical form, fill, seal belts for bagger machines, Pharmaceutical industry, Paper / Cardboard conveying

General remarks

Abrasion resistant even in wet conditions, high elasticity, constantly high friction. Good release properties to conveyed goods, e.g. foodstuff.