

# siegling proposition timing belts

# Coating Data Sheet



### Designation

Coating type description OLD	PU foil 60
Coating type description NEW	PU 60

### Design

Coating Material	Polyurethane (thermoplastic)
Colour	Transparent
Surface pattern	Smooth (sanded)

### **Technical data**

Hardness [Shore(A)]	60
Density [kg/m³]	
Coating thickness min. [mm]	2.0
Coating thickness max. [mm]	4.0
d factor *	25
Minimum pulley diameter D <sub>min</sub> (approx.) [mm]	[d factor] x [selected coating thickness]
Minimum operating temperature [°C]	-20
Maximum operating temperature [°C]	80

### Coefficient of static friction

against PE foil	0.85	
against wood	1.10	
against sheet glass	1.13	
against cardboard	0.76	
against aluminium	1.10	
against steel sheet	1.42	



# siegling proposition timing belts

# Coating Data Sheet

### **Properties**

Electrostatic properties	non-conductive
Wear resistance	medium
Compressibility	No
Product release properties	good release
Cleanability	good

### **Chemical restistance**

General chemical resistance to	Generic fats and oils

### **Special Fabrication**

Sanding	Yes
Milling	Yes
Punching	Yes

## **Applications**

Glass conveying, Paper / Cardboard conveying, Conveying of abrasive goods

## **General remarks**

High chemical resistance in general. Good release properties.