

# siegling proposition timing belts

## Coating Data Sheet







Coating Material	Polyurethane (thermoplastic)
Colour	Transparent
Surface pattern	Longitudinal groove profile

#### **Technical data**

Hardness [Shore(A)]	85
Density [kg/m³]	
Coating thickness min. [mm]	2.0
Coating thickness max. [mm]	4.0
d factor *	30
Minimum pulley diameter D <sub>min</sub> (approx.) [mm]	[d factor] x [selected coating thickness]
Minimum operating temperature [°C]	-20
Maximum operating temperature [°C]	80

#### Coefficient of static friction

against PE foil	1.15
against wood	0.89
against sheet glass	1.31
against cardboard	0.80
against aluminium	1.28
against steel sheet	1.30





## siegling proposition timing belts

## Coating Data Sheet

#### **Properties**

Electrostatic properties	non-conductive
Wear resistance	high
Compressibility	No
Product release properties	medium
Cleanability	effortful

#### **Chemical restistance**

General chemical resistance to	Generic fats and oils

#### **Special Fabrication**

Sanding	No
Milling	No
Punching	Yes

#### **Applications**

Glass conveying, General conveying, Conveying of abrasive goods

### **General remarks**

High chemical and abrasion resistance in general.